## Effect of calcination Temperature on Selective Catalytic Reduction over Manganese Oxides at Low Temperature

<u>정순관</u>\*, 박영옥, 홍성창<sup>1</sup> 한국에너지기술연구원; <sup>1</sup>경기대학교 환경공학과 (jeongsk@kier.re.kr\*)

Natural manganese ore (NMO) exhibits the great activity for the selective catalytic reduction (SCR) of nitrogen oxides with ammonia at low temperatures. The catalytic behavior of NMO which consists mainly of manganese oxides depends strongly on the calcination temperature. It was found that the optimum calcination temperature is  $300 - 400^{\circ}$ C. Due to decrease of the activated surface by carbon impurities dried at  $120^{\circ}$ C, DeNOx was so poor. Meanwhile, the deficiency of oxygen for the redox function in the catalyst calcined at over  $500^{\circ}$ C mghit result in low activity. In the presence of water, SCR activity decreased due to the competitive adsorption between water and ammonia, because water inhibit the adsorption for both NO and NH<sub>3</sub>

화학공학의 이론과 응용 제9권 제2호 2003년