Highly Active Mesoporous  $\mathrm{RuO}_2$  catalyst Pretreated with  $\mathrm{O}_2$  for Room temperature CO oxidation

<u>김명실</u>, 이정화, 김지만\* 성균관대학교 (jimankim@skku.edu\*)

Highly ordered mesoporous ruthenium dioxide (meso-RuO<sub>2</sub>) has been successfully synthesized by controlling the surface hydrophobicity of mesoporous silica template (KIT-6) via a nano-replication method. The meso-RuO<sub>2</sub>) material, thus obtained, exhibits a well-defined mesostructure and high surface area (131 m² g-1). Pretreatment of the meso-RuO<sub>2</sub> catalyst under different gas environments (O<sub>2</sub>, H<sub>2</sub> and CO) strongly affects the catalytic activity towards CO oxidation. The meso-RuO<sub>2</sub>, pretreated by O<sub>2</sub> flowing at 200 °C, exhibited excellent catalytic activity for CO oxidation, 100% CO conversion with long-term stability at room temperature, whereas the meso-RuO<sub>2</sub> catalysts with pretreatment under other conditions are not very active at room temperature. It is found that the surface oxygen species, generated on the meso-RuO<sub>2</sub> during O<sub>2</sub> pretreatment at 200 °C, provide CO oxidation activity at room temperature.